

# Turbo-Coat™ HV Acrylic Conformal Coating

**2109****2110 (Turbo-Coat Thinner)**

## Introduction

---



Techspray's new Turbo-Coat™ HV Acrylic Conformal Coating is a high viscosity version of our popular Turbo-Coat. This coating is tested and approved in Asymtek and PVA selective spray systems, both atomized and airless models.

Turbo-Coat is designed to speed up board production throughput without additional investment of expensive UV systems or other capital equipment. Conformal coating cure time is often considered a production bottleneck for PCB assembly operations. Turbo-Coat HV dries tack-free in under 10 minutes, allowing manufactures to handle boards in 1/2 the time of the leading acrylic coating!

Turbo-Coat Thinner is available to reduce the viscosity to fit ideal process parameters. Turbo-Coat, Turbo-Coat HV, and Turbo-Coat Thinner are all HAPs (Hazardous Air Pollutants) free, so do not contain common coating solvents like Toluene, Xylene, and MEK. This makes these coating more user friendly and safe.

Turbo-Coat HV uses the same acrylic resin as the original Turbo-Coat, so coatings can be mixed-and-matched through the process, e.g. using the faster curing Turbo-Coat in the rework area, Turbo-Coat HV in the assembly area, and Turbo-Coat pen for QC touch-up.

### Features / Benefits

- Fastest Cure – Dry to Touch in Under 10 Minutes!
- Faster Throughput without Capital Investment
- Thick Coating – One-Pass Application
- Fast & Easy Rework & Repair
- IPC-CC-830B& MIL-I-46058C Certified
- UL94 V-0 Rated
- Crystal Clear & Glossy Finish
- UV Indicator for Black Light QC Inspection
- MEK, Toluene & Xylene Free

### Applications

Electronic Assemblies for...

- Automotive
- Aviation
- Consumer Electronics
- Appliances
- Industrial Meters & Control

### Thinning / Removal

Techspray coatings can be thinned to meet production requirements using Turbo-Coat Thinner (2110). Conformal Coating Remover (2510) is also available for rework and repair, although coating is often just burnt through in the soldering process for spot repairs.

Techspray coatings contain Opti/Scan to allow quality control inspection of coverage and evenness of the coating on a PCB. A coated board can be passed under a standard, low-cost long-wave UV (black) light, and the coated areas glow. The brighter the glow, the thicker the coating.

## Chemical Components

### **TURBO-COAT HV (2109)**

Chemical	CAS #
Acrylic Polymer (non-hazardous)	
tert-Butyl acetate.....	540-88-5
n-butyl acetate .....	123-86-4
1-Methoxy-2-propanol.....	107-98-2
1-(2-Methoxy-Methyl-Ethoxy)-2-Propanol Acetate.....	88917-22-0

### **TURBO-COAT THINNER (2110)**

Chemical	CAS #
n-butyl acetate .....	123-86-4
propylene glycol monomethyl ether .....	107-98-2

## Cure Profile

<b>Accelerated Cure:</b>	55 minutes @ 131°F / 55°C
<b>Ambient Cure:</b>	15 hours @ 74°F / 23°C (ambient temp)
<b>Tack-Time (dry to touch):</b>	9 minutes @ 74°F / 23°C (ambient temp)

Cure time depends on a number of factors, including the method and thickness of application. Dilution will also change the cure profile. 131°F / 55°C is recommended as the best accelerated temperature to optimize leveling, providing the smoothest possible finish. A faster cure may be achieved, but should be thoroughly tested first.

## Test Data

### Application

	Test Method*	2109 Test Results
Application Method		Spray system, dip, or brush
Cure time	TS-053	<15 hrs
Accelerated cure time	TS-054	55 Min. @ 55°C
Dry time to touch	TS-055	9 Min.
Quality inspection method of coverage		UV (long-wave black) light
Removal method		Alkane, Acetone or Acetate, Solder iron burn through

### Characteristics

As Supplied:	Test Method	2109 Test Results
Visual appearance	TS-050	Clear
Density (25 C)	TS-019-1	0.91
Viscosity (25 C)	Instrument (Brookefield RVT) guide	53 to 60 Centipoise
Solids %	TS-015	24-26
Flash point	ASTM D-56 (TAG CC)	5°C (41°F)
Vapor pressure (20 C) (VOC composite)	calculated	1.12 mmHg
Initial boiling point	TS-051	Not Determined
Stability (30-day test @ 37 C/100 F)	TS-052	Stable
Stability (30-day test @ 6.1 C/21 F)	TS-052-1	Stable
Resin T <sub>g</sub>	provided by supplier	50 – 55 C
Resin mol wt	provided by supplier	60,000

Certified Testing – pending, stated results based on 2108, which contains the same resin

<b>As Cured - Physical</b>	<b>Test Method</b>	<b>2109 Test Results</b>
Dielectric strength	ASTM D-149, IPC-TM-650 2.5.6.1, Rev. A	1000 volts
Adhesion	ASTM D-3359	5B
Film hardness	ASTM D-3363	2B
Film thickness (1 dip)	ASTM D-1005	1 mil (0.001")
<b>UL Qualification</b>	<b>Test Method</b>	<b>2109 Test Results</b>
Coating flammability	UL94/746E	V-0
<b>IPC-CC-830B Qualification</b>	<b>Test Method</b>	<b>2109 Test Results</b>
Appearance	IPC-CC-830B 3.5.2	pass
Fluorescence	IPC-CC-830B 3.5.3	pass
Flammability	IPC-CC-830B 3.5.6	pass
Fungus resistance*	IPC-TM-650 2.6.1.1	pass
Flexibility	IPC-TM-650 2.4.5.1	pass
Dielectric withstand voltage	IPC-TM-650 2.5.7.1	pass
Moisture & insulation resistance*	IPC-TM-650 2.6.3.4	pass
Thermal shock*	IPC-TM-650 2.6.7.1	pass
Temperature humidity ageing*	IPC-TM-650 2.6.11.1	pass

\* Final results for 2109 pending. Results based on 2108, which uses the same resin. All other specification testing is complete.

#### Chemical Compatibility – Industrial Chemicals

<b>INDUSTRIAL CHEMICALS</b>	<b>EFFECT</b>	<b>CAS #</b>
Methanol	Soften	67-56-1
Ethanol	Dissolution	64-17-5
IPA	Dissolution	67-63-0
70% IPA	Dissolution	67-63-0
50% Ethanol	No effect	64-17-5
DPM	Dissolution	34590-94-8
Glycol ether EB	Dissolution	111-76-2
THF	Dissolution	109-99-9
Acetone	Dissolution	67-64-1
n-propyl acetate	Dissolution	109-60-4
t-butyl acetate	Dissolution	540-88-5
Hexane	Dissolution	110-54-3
Heptane	Soften	142-82-5
Cyclopentane	Dissolution	287-92-3
Cyclohexane	Dissolution	110-82-7
Toluene	Dissolution	108-88-3
Trans-dce	Dissolution	156-60-5

## Chemical Compatibility – Household Chemicals

HOUSEHOLD CHEMICALS	EFFECT	EXAMPLE OF US BRAND NAME
5% Acetic acid	No effect	Heinz Vinegar
0.1N Hydrochloric acid	No effect	Lime-A-Way Toilet Bowl Cleaner
50% Nitric acid	No effect	
Parson's solution	No effect	Windex
0.1N Potassium hydroxide	No effect	10% Liquid Plumber
45% Potassium hydroxide	No effect	Liquid Plumber
d-limonene	Dissolution	Orange Glo
Chlorox neat	No effect	Chlorox
Chlorox 1:1	No effect	50% Chlorox
Chlorox 1:4	No effect	20% Chlorox
Pine-Sol Lemon	No effect	Pine-Sol Lemon
Pro 409	No effect	409 Professional

*In most cases, Techspray corporate test methods (TS designation) correspond to standard ASTM Copies of Techspray corporate test methods are available upon request.*

## Environmental Policy

---

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

## Packaging and Availability

---

### Turbo-Coat HV:

2109-P	1 pint (0.47L) in glass bottle
2109-G	1 gallon (3.8L) in metal bottle
2109-5G	5 gallons (18.9L) in metal pail
2109-54G	54 gallons (204L) in metal drum

### Turbo-Coat Thinner:

2110-G	1 gallon (3.8L) in metal bottle
2110-5G	5 gallons (18.9L) in metal pail

### Original Turbo-Coat:

2108-12S	12oz aerosol
2108-P	1 pint (0.47L) in glass bottle
2108-G	1 gallon (3.8L) in metal bottle
2108-5G	5 gallons (18.9L) in metal pail

## Resources

---

Techspray® products are supported by a global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email [tsales@techspray.com](mailto:tsales@techspray.com) or visit our web site at: [www.techspray.com](http://www.techspray.com).

North America  
Techspray  
P.O. Box 949  
Amarillo, TX 79105  
800-858-4043  
email: [tsales@techspray.com](mailto:tsales@techspray.com)

Europe  
ITW Contamination Control BV  
Saffierlaan 5  
2132 VZ Hoofddorp  
The Netherlands  
+31 88 1307 400  
[info@itw-cc.com](mailto:info@itw-cc.com)

Countries Outside US  
Call to locate a distributor  
in your country.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.