



Ti900

Thermally Conductive Insulators

Version 2.130218

Thermal Conductive Insulators

Ti900 is a high thermal performance insulator pad designed to maximize thermal conductivity and electrical isolation performance for a wide variety of applications. The unique formulation offers a smooth and compliant surface which minimizes interfacial thermal resistance at low mounting forces.

Features

- High insulation strength
- Low thermal resistance
- Die cut for custom shapes
- Easy to assemble

Applications

Electronic components: IC, CPU, MOS
 LED, M/B, P/S, Heat Sink
 LCD, TV, Notebook PC, PC Telecom Device, Wireless, etc.
 DDR II Module, DVD Applications, Hand-set applications, etc.

Properties

- ✓ REACH Compliant
- ✓ ROHS Compliant

Property	Ti900	Unit	Test Method
Viscose	One Side	-	ASTM D374
Thickness	0.12	mm	-
Base	RITF	-	-
Thermal Conductivity	1.8	W/mK	ASTM D5470
Thermal Resistance @ 10psi	0.50	K in ² /W	ASTM D5470
Thermal Resistance @ 30psi	0.42	K in ² /W	ASTM D5470
Thermal Resistance @ 50psi	0.35	K in ² /W	ASTM D5470
Thermal Resistance @ 100psi	0.29	K in ² /W	ASTM D5470
Thermal Resistance @ 200psi	0.28	K in ² /W	ASTM D5470
Thermal Resistance @ 400psi	0.27	K in ² /W	ASTM D5470
Insulation Strength Vac, V	>6000	-	ASTM D149
Volume Resistance	>10 ¹²	Ohm-cm	ASTM D257
Working Temperature	-50 to 180	oc	-
Tensile Strength	5000	psi	ASTM D412
Elongation	40	%	ASTM D412
Flammability Rating	V-0	-	UL94
Shelf Life	36	months	-
Shelf Life with adhesive (can be requalified for further 12)	12	months	-

T-Global Technology Limited
 1 & 2 Cosford Business Park, Central Park,
 Lutterworth, Leicestershire LE17 4QU U.K.

Tel: +44 (0)1455 553 510
 Email: sales@tglobaltechnology.com
 Web: www.tglobaltechnology.com
 Skype: tglobal.technology
 VAT #: GB 116 662 714



Ti900

Thermally Conductive Insulators

Standard Weights & Dimensional Tolerance

Size	Thickness (mm)	0.12
	100x100	0.96
	150x150	2.16
	300x300	8.64
	320x320	9.83

* All measurements in weights are in gr

** All sizes are in mm

Die-Cut Thickness Tolerances	Thickness (mm)	Tolerance (mm)
	0.3	±0.03
	0.5	±0.05
	0.8	±0.08
	1.0	±0.1
	1.2	±0.12
	1.5	±0.15
	2.0	±0.2
	2.5 - 3.5	±0.25
	4.0 - 4.5	±0.3
	5.0	±0.35
	6.0 - 8.0	±0.4
	9.0	±0.45
	10.0	±0.5
>10.0	±0.5	

* Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

NOTICE: The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology Europe and North America's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.