

LOCTITE[®] EA 9461

Known as Hysol 9461
September 2016

PRODUCT DESCRIPTION

LOCTITE[®] EA 9461 provides the following product characteristics:

Technology	Epoxy
Chemical Type (Resin)	Epoxy
Chemical Type (Hardener)	Amine
Appearance (Resin)	White opaque paste
Appearance (Hardener)	Black opaque paste
Appearance (Mixture)	Gray paste
Components	Two part - Resin & Hardener
Viscosity	Thixotropic
Mix Ratio, (by volume) Resin : Hardener	1 : 1
Mix Ratio, by weight - Resin : Hardener	100 : 100
Cure	Room temperature cure after mixing
Application	Bonding
Maximum Gap	3.0 mm
Specific Benefits	<ul style="list-style-type: none"> • Excellent peel strength • Excellent shear strength • Impact and fatigue resistant • Non-sag slump resistance • Easy to mix and dispense

LOCTITE[®] EA 9461 is a thixotropic, two component epoxy adhesive formulated for ease of use as well for a good balance of properties. This adhesive couples high peel strength and excellent shear strength in a smooth, non-sag paste that is easily dispensed. The product has a medium working life with a quick heat cure response if required. The tough nature of this structural adhesive makes it useful for bonding dissimilar substrates including metals, engineering thermoplastics and thermoset laminates such as sheet moulding compound (SMC).

TYPICAL PROPERTIES OF UNCURED MATERIAL

Resin Properties

Specific Gravity @ 25 °C	1.35
Viscosity, DIN 54453, mPa·s (cP):	
Shear rate 10 s ⁻¹	85,980
Shear rate 50 s ⁻¹	38,570
Thixotropic Index	2.8

Flash Point - See SDS

Hardener Properties

Specific Gravity @ 25 °C	1.31
Viscosity, DIN 54453, mPa·s (cP):	
Shear rate 10 s ⁻¹	59,530
Shear rate 50 s ⁻¹	42,860
Thixotropic Index	2
Flash Point - See SDS	

Mixed Properties

Pot Life @ 22°C, minutes:	
100 g mass	40

TYPICAL CURING PERFORMANCE


Fixture Time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

Fixture Time, mixed, @ 22°C, minutes	240
--------------------------------------	-----

Cure Speed vs. Time/Temperature

LOCTITE[®] EA 9461 will achieve handling strength in 4 to 5 hours at room temperature (note: this can vary with different bond configurations and ambient temperatures). Elevated temperatures may be used to accelerate the cure. The graph below shows the shear strength developed with time on grit blasted steel lap shears at different temperatures and tested according to ISO 4587.



TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 7days @ 22°C, 1.2 mm thick samples

Physical Properties :

Shore Hardness, ISO 868, Durometer D	80
Elongation , ISO 527-2,%	3.5
Tensile Strength, ISO 527-2	N/mm ² 30 (psi) (4,400)
Tensile Modulus , ISO 527-2	N/mm ² 2,757 (psi) (400,000)

Electrical Properties :

Dielectric Strength, kV/mm	36.6
Dielectric Constant / Dissipation Factor :	
@ 1 KHz	4.1/0.023
@ 1MHz	3.8/0.04
@ 10MHz	3.6/0.057
Surface Resistivity, IEC 60093, ohms	≥1.9×10 ¹⁷
Volume Resistivity, IEC 60093, ohm-cm	1.8×10 ¹⁴

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 7days @ 22°C

Lap Shear Strength , ISO 4587:

Mild steel (grit blasted)	N/mm ² 25 (psi) (3,600)
Aluminum (abraded)	N/mm ² 21 (psi) (3,100)
(Silicon Carbide Paper, A166 grit, P400A grade)	
Aluminum (etched in acidic ferric sulphate)	N/mm ² 21 (psi) (3,100)
Stainless steel	N/mm ² 19 (psi) (2,800)
Galvanized Steel (Hot Dipped)	N/mm ² 16 (psi) (2,300)
Brass	N/mm ² 11 (psi) (1,600)
Zinc dichromate	N/mm ² 16 (psi) (2,300)
Polycarbonate	N/mm ² 6.5 (psi) (940)
ABS	N/mm ² 6.2 (psi) (900)
GRP (Polyester resin matrix)	N/mm ² 5 (psi) (720)
Glass Fiber Reinforced Epoxy	N/mm ² 13 (psi) (1,900)

180° Peel Strength, ISO 8510-2:

Mild Steel (grit blasted)	N/mm 10 (lb/in) (57.1)
---------------------------	---------------------------

IZOD Impact Resistance , ISO 9653 J/m² :

Mild Steel (grit blasted)	8.3
---------------------------	-----

TYPICAL ENVIRONMENTAL RESISTANCE


Cured for 7days @ 22°C

Lap Shear Strength , ISO 4587:

Mild Steel (grit blasted)	
---------------------------	--

Hot Strength

Tested at temperature



Heat Aging

Aged under conditions indicated and tested at 22 °C.

Temperature	% Initial strength retained after		
	500 h	1,000 h	3,000 h
50 °C	110	105	105
80 °C	115	125	120
100 °C	110	100	100
120 °C	125	125	125
150 °C	135	125	120

Chemical/Solvent Resistance

Immersed in conditions indicated and tested at 22 °C.

Environment	°C	% of initial strength		
		500 h	1000 h	3000 h
Motor oil	22	100	95	100
Unleaded gasoline	22	75	70	60
Water/glycol 50/50	87	75	75	95
Sodium hydroxide, 4%	22	85	80	80
98% RH	40	85	70	70
Water	60	85	75	75
Water	90	85	80	55
Acetone	22	65	35	35
Acetic Acid, 10%	22	75	65	50
Salt water solution, 7.5%	22	80	80	80

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

Directions for use

1. For best performance surfaces for bonding should be clean, dry and free of grease. For high strength structural bonds, special surface treatments can increase the bond strength and durability.
2. To use, resin and hardener must be blended. Product



can be applied directly from dual cartridges by dispensing through the mixer head supplied. Discard the first 3 to 5 cm of bead dispensed. Using bulk containers, mix thoroughly by weight or volume in the proportions specified in the Product Description Matrix.

For hand mixing, weigh or measure out the desired amount of resin and hardener and mix thoroughly. Mix approximately 15 seconds after uniform color is obtained.

3. It is recommended that this product is not mixed and cured in bulk quantities of greater than 4 kg as excessive heat build-up can occur. Mixing smaller quantities will minimize the heat build-up.
4. Apply the adhesive as quickly as possible after mixing to one surface to be joined. For maximum bond strength apply adhesive evenly to both surfaces. Parts should be assembled immediately after mixed adhesive has been applied.
5. For working life please see section 'Typical Properties of Uncured Material'. Higher temperatures and larger quantities will shorten this working time.
6. Keep the assembled parts from moving during cure. The joint should be allowed to develop full strength before subjecting to any service loads.
7. Excess uncured adhesive can be wiped away with organic solvent (e.g. Acetone).
8. After use and before adhesive hardens, mixing and application equipment should be cleaned with hot soapy water.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$

$\text{N/mm}^2 = \text{MPa}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose,**



arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.3

