



Thermogrip® H2224

HOT MELT ADHESIVE

KEY FEATURES

- Good bond to polyolefins
- Excellent die-cutting
- Light Color

DESCRIPTION

H2224 is a pressure sensitive hot melt adhesive with medium viscosity. It is light colored, with excellent die-cutting, and bonds to polyolefins from 30 to 110°F.

PACKAGING

For packaging options please call your Bostik sales or technical representative.

SHELF LIFE

Can be stored 730 days in a clean dry place, in its original package at an average temperature of 25°C or below. Storage temperature should not exceed 40°C.

STORAGE & HANDLING

Wear safety gloves and goggles when handling molten adhesive to minimize the risk of burns.

COUNTRY OF MANUFACTURE

United States

CLEANUP PROCEDURE

Mineral oil or paraffin wax are recommended for cleanup but should not be used at temperatures that exceed the flash point as stated on the SDS. This procedure should be followed by a thorough purge with the adhesive.

FDA 21 CFR NUMBERS

Please contact your Bostik Representative regarding the suitability of this product for use in applications where direct or indirect food contact is expected.



JUICE JUGS

MILK JUGS

TYPICAL PHYSICAL PROPERTIES

Description	Results
Thermosel Viscosity (Brookfield - ASTM D3236)	15,700 cP @ 300 °F (149 °C) 9,100 cP @ 325 °F (163 °C) 5,750 cP @ 350 °F (177 °C)
Softening Point - Ring and Ball (Herzog - ASTM E28)	200 °F (93 °C)
Suggested Running Temperature	325 - 355 °F (163 - 179 °C)
Density	0.94 g/cc @ 77 °F (25 °C)


BASIC USES

H2224 is used for labels to be applied at lower temperatures to polyolefin surfaces. H2224 can be used on milk and juice jugs.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet should be consulted for proper handling, clean up and spill containment before use. Keep containers covered to minimize contamination.

VISCOSITY CURVE



LIMITED WARRANTY

The Limited Warranty for this product can be found at www.bostik-us.com/resource-center/warranties or by calling 1-800-726-7845 (choose option 2, then option 2 again). To the maximum extent allowed by law, Bostik disclaims all other express or implied warranties, including without limitation warranties of merchantability and fitness for a particular purpose. Unless otherwise stated in the limited warranty, the sole remedy for breach of warranty is replacement of the product or refund of the buyer's purchase price. Bostik disclaims any liability for direct, incidental, consequential, or special damages to the maximum extent allowed by law. Disclaimers of implied warranties may not be applicable to certain classes of buyers and some states do not allow the exclusion or limitation of incidental or consequential damages, so the above limitations may not apply to you. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. The Limited Warranty extends only to the original purchaser and is not transferable or assignable. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

BOSTIK HOTLINE

Smart help
1-800-726-7845

Bostik, Inc.
11320 W. Watertown Plank Road
Wauwatosa, WI 53226
www.bostik-us.com



This document supersedes all previously published literature.
02.05.2016