

# LOCTITE<sup>®</sup> EA 3981

Known as LOCTITE<sup>®</sup> 3981  
September 2020

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> EA 3981 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Chemical Type</b>	Epoxy
<b>Appearance (uncured)</b>	Translucent, slight amber liquid <sup>LMS</sup>
<b>Appearance (cured)</b>	Translucent, slight amber solid <sup>LMS</sup>
<b>Fluorescence</b>	Positive under UV light
<b>Components</b>	One component - requires no mixing
<b>Cure</b>	Heat cure
<b>Cure Benefit</b>	Production - high speed curing
<b>Application</b>	Assembly of disposable medical devices.
<b>Key Substrates</b>	Stainless steel and Plastics

LOCTITE<sup>®</sup> EA 3981 is suitable for a wide range of applications that require fast cure, excellent environmental resistance and high adhesion. The product cures rapidly when exposed to temperatures as low as 100 °C and achieves excellent adhesion to plastics, metals and glass. LOCTITE<sup>®</sup> EA 3981 was specifically designed for bonding stainless steel cannulae into hubs, syringes and lancets for needle assemblies. Suitable for use in the assembly of **disposable medical devices**.

## ISO-10993

LOCTITE<sup>®</sup> EA 3981 has been tested to Henkel's test protocols based on ISO 10993 biocompatibility standards, as a means to assist in the selection of products for use in the medical device industry.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.14
Flash Point - See SDS	
Viscosity, Brookfield SSA - RVT, 25°C, mPa·s (cP):	
Spindle 14, speed 50 rpm	4,000 to 6,000 <sup>LMS</sup>

## TYPICAL CURING PERFORMANCE

### Cure Schedule

Typical cure times were estimated as >99% conversion using differential scanning calorimetry:

- @ 100 °C, 35 minutes
- @ 125 °C, 23 minutes
- @ 150 °C, 16 minutes

## TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 30 minutes @ 120°C

### Physical Properties:

Shore Hardness, ISO 868 , Durometer D  $\geq 70^{\text{LMS}}$

Cured for 30 minutes @ 125 °C.

### Physical Properties:

Coefficient of Thermal Expansion, ISO 11359-2, K <sup>-1</sup> :	
Pre Tg (Alpha 1)	62×10 <sup>-6</sup>
Post Tg (Alpha 2)	193×10 <sup>-6</sup>
Glass Transition Temperature, ASTM E 228, °C	56
Linear Shrinkage, in/in ASTM D 792,	1.4
Water Absorption, ISO 62, %:	
2 hours in boiling water	1.8
7days in water @ 22 °C	0.63
Elongation, at break, ISO 527-3, %	2.98
Tensile Strength, ISO 527-3	N/mm <sup>2</sup> 62 (psi) (8,970)
Tensile Modulus, ISO 527-3	N/mm <sup>2</sup> 2,383 (psi) (345,500)

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Adhesive Properties

Cured for 30 minutes @ 120 °C.

Lap Shear Strength, :

Aluminum (etched):	
0.125 mm gap	N/mm <sup>2</sup> $\geq 13.8^{\text{LMS}}$ (psi) ( $\geq 2,000$ )

Cured for 30 minutes @ 100 °C.

**Needle Pullout Strength:**

Material	22 Gauge Cannula	27 Gauge Cannula:
ABS	N 302 (lb) (68)	N 147 (lb) (33)
Acrylic	N 276 (lb) (62)	N 142 (lb) (32)
Polycarbonate	N 89 (lb) (20)	N 76 (lb) (17)
Polyethylene	N 13 (lb) (3)	N 13 (lb) (3)
Polyethylene (plasma treated)	N 214 (lb) (48)	N 138 (lb) (31)
Polypropylene	N 18 (lb) (4)	N 13 (lb) (3)
Polypropylene (plasma treated)	N 160 (lb) (36)	N 98 (lb) (22)
Polystyrene	N 191 (lb) (43)	N 125 (lb) (28)
Polyurethane	N 280 (lb) (63)	N 151 (lb) (34)

Cured for 30 minutes @ 125 °C.

**Block Shear Strength, ISO 13445:**

Acrylic	N/mm <sup>2</sup> 4 (psi) (580)
G-10 Epoxy	N/mm <sup>2</sup> 15 (psi) (2,240)
Nylon	N/mm <sup>2</sup> 4 (psi) (620)
Polybutylene Terephthalate	N/mm <sup>2</sup> 12 (psi) (1,670)
Polycarbonate	N/mm <sup>2</sup> 3 (psi) (370)
Aluminum (grit blasted)	N/mm <sup>2</sup> 29 (psi) (4,160)
Steel (grit blasted)	N/mm <sup>2</sup> 34 (psi) (4,930)

**TYPICAL ENVIRONMENTAL RESISTANCE**

**Thermal Stability of Needle Assemblies**

Aged @ 60°C and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:

Plastic:	4 Weeks	8 Weeks:
Polycarbonate:		
22 Gauge Cannula	255	290
27 Gauge Cannula	175	205
Polypropylene (plasma treated):		
22 Gauge Cannula	170	180
27 Gauge Cannula	170	160
Polystyrene:		
22 Gauge Cannula	125	110
27 Gauge Cannula	120	125

**Sterilization Resistance of Needle Assemblies**

Sterilized as indicated and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:


Plastic	Gamma 30 kGy	ETO 1 cycle	Autoclave 1 cycle 5 cycles	
Polycarbonate:				
22 Gauge Cannula	110	110	90	90
27 Gauge Cannula	100	100	60	75
Polypropylene (plasma treated):				
22 Gauge Cannula	145	140	75	85
27 Gauge Cannula	140	110	65	100
Polystyrene:				
22 Gauge Cannula	100	100	N/A	N/A
27 Gauge Cannula	95	90	N/A	N/A

N/A - Not Applicable. The polystyrene was not compatible with the autoclave sterilization process.

**Hot Strength**

Cured for 30 minutes @ 125 °C. The bonded specimens were tested at the indicated temperature:


Block Shear Strength, ISO 13445, Polycarbonate



**Heat Aging**

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate



**Chemical/Solvent Resistance**

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate

Environment	°C	% of initial strength			
		24 h	100 h	500 h	1000 h
95% RH	40	-----	140	170	170
Ambient Water Submersion	22	-----	160	160	115
Isopropanol	22	150	-----	-----	-----
Heptane	22	140	-----	-----	-----

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Directions For Use:**

1. Adhesive must be room temperature just prior to use.
2. Clean and dry surfaces to be bonded.
3. Apply adhesive evenly to both surfaces.
4. Assemble parts and allow to cure at 100 °C for 35 minutes or until completely firm.
5. Refer to cure schedule for alternate cure information.

**Loctite Material Specification<sup>LMS</sup>**

LMS dated August 08, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.4